

## Preparation of zinc peroxide nanoparticles by laser ablation of solid in liquids

Palma-Palma H. E.

*Maestría en Ciencia de Materiales, Facultad de Química Universidad Autónoma del Estado de México  
Paseo Colón esq. Paseo Tollocan SN, 50120 Toluca de Lerdo, Estado de México*

Camacho-López M.\*

*Laboratorio de Investigación y Desarrollo de Materiales Avanzados, Facultad de Química, Universidad Autónoma del Estado de México, Campus Rosedal, Km 14.5 Carretera Toluca-Atlacomulco, San Cayetano de Morelos C.P. 50925*

Camacho-López M. A.

*Laboratorio de Fotomedicina, Biofotónica y Espectroscopía Láser de Pulso Ultracortos, Facultad de Medicina,  
Universidad Autónoma del Estado de México  
Jesús Carranza y Paseo Tollocan s/n. Toluca, México, C.P. 50120*

Vilchis-Néstor A. R.

*Centro Conjunto de Investigación en Química Sustentable UAEM-UNAM  
Facultad de Química, Universidad Autónoma del Estado de México  
Carretera Toluca-Atlacomulco, San Cayetano, México*  
(Recibido: 15 de marzo de 2015; Aceptado: 3 de agosto de 2015)

We report the preparation of zinc peroxide nanoparticles ( $ZnO_2$  NPs) by the laser ablation of solid in liquids technique. Experiments were performed by using the fundamental wavelength (1064 nm) of a pulsed nanosecond Nd:YAG laser operated at a repetition rate of 15 Hz. A Zn disk (99.99 % purity) were the target and 10 ml of 30%  $H_2O_2$  solution was used as liquid medium. The per pulse laser fluence was varied. In all the experiments the ablation time was 10 min. The samples were characterized by Raman microspectroscopy, Calorimetry and TEM. Results show that  $ZnO_2$  NPs were successfully obtained by this method of preparation.

**Keywords:** Laser ablation;  $ZnO_2$ ; Raman


### 1. Introduction

In the last decade, there has been interest on the synthesis and characterization of Zinc peroxide ( $ZnO_2$ ) due to its potential applications as biocide, bactericide, inorganic oxidant and so on [1-3].  $ZnO_2$  can be obtained as a powder with a cubic structure and has been utilized as a precursor to obtain Zinc oxide ( $ZnO$ ).  $ZnO_2$  can be considered as an oxygen reservoir since when it is heated at relatively low temperatures oxygen is released.


Various approaches have been utilized to synthesize  $ZnO_2$  powders like sol-gel, organometallic precursors, hydrothermal, Laser Ablation of Solids in Liquids (LASL), and so on [4-16]. While the hydrothermal route is one of the most utilized methods to obtain  $ZnO_2$ , the LASL technique has only been utilized by the Gondal's group to synthesize zinc peroxide nanoparticles [11-12]. Escobedo *et al.* have been reported a study of the vibrational properties of  $ZnO_2$  NPs synthesized by the hydrothermal method. Additionally, they present results of XRD, TEM and by thermal analysis determine the decomposition temperature of their  $ZnO_2$  NPs [8]. Recently, the Escobedo-Morales's group has reported a green method to prepare  $ZnO$  nanostructures employing as starting material  $ZnO_2$  (prepared by hydrothermal method) [17].

LASL is a green technique that has been utilized to prepare metal, semiconductor and ceramic nanostructures [18-19]. This method is experimentally simple and has been used to obtain metal oxides based colloidal solutions like Zinc oxide, Molybdenum Oxide, Bismuth Oxide, Tin Oxide [11, 12, 20-22]. Gondal *et al.* have reported the synthesis of  $ZnO_2$  NPs colloidal solutions by using the LASL technique. They have performed their experiments with the third harmonic of a Nd:YAG laser emitting at 355 nm, a foil of Zinc as target and 3% hydrogen peroxide ( $H_2O_2$ ) solution as liquid medium. Gondal *et al.* have reported that the band gap of  $ZnO_2$  NPs can be within the range 3.0-3.6 eV [12]. With the aim to study the properties of  $ZnO_2$  NPs obtained by LASL it is necessary to perform experiments with other ablation parameters such as the emitting wavelength (1064 nm) of the Nd:YAG laser and its per pulse laser fluence. To the best of our knowledge, only the work of Gondal *et al.* has reported the synthesis of  $ZnO_2$  by LASL technique.

In this work we present results on the characterization of  $ZnO_2$  NPs obtained by LASL technique. A pulsed Nd:YAG laser emitting at 1064 nm, metallic Zinc disk and  $H_2O_2$  solution were used to prepare the  $ZnO_2$  NPs. The samples were characterized by Raman microspectroscopy, calorimetry and TEM. Results show that LASL is a suitable technique to prepare  $ZnO_2$  NPs.



**Figure 1.** (a) Experimental Set-Up to ablate Zn in  $\text{H}_2\text{O}_2$  liquid medium, (b) Photograph of a 30%  $\text{H}_2\text{O}_2$  solution (left),  $\text{ZnO}_2$  based colloidal  $\text{H}_2\text{O}_2$  solution obtained at a per pulse laser fluence of 22  $\text{J}/\text{cm}^2$  by laser ablation during 10 min (center) and  $\text{ZnO}_2$  based colloidal  $\text{H}_2\text{O}_2$  solution left to rest for 1 hour (right).



**Figure 2.** Raman Spectra of the  $\text{ZnO}_2$  obtained by ALSL at a per pulse laser fluence of (a) 8, (b) 13, (c) 19 and (d) 22  $\text{J}/\text{cm}^2$ .

## 2. Experimental

### 2.1. Sample preparation

Figure 1(a) shows the experimental set-up to obtain  $\text{ZnO}_2$  NPs by LASL technique. Nanosecond (ns) laser pulses ( $7 \pm 2$  ns pulse duration) from a Nd:YAG laser (Minilite II, Continuum) were used to ablate the Zn disk (2.54 cm in diameter, 0.375 cm thick, and 99.99 % purity, Kurt J. Lesker Co.); 10 ml of 30%  $\text{H}_2\text{O}_2$  solution was used as liquid medium in each ablation experiment. The laser was operated in its fundamental emission wavelength (1064 nm) at 15 Hz repetition rate. The per pulse laser fluence was varied by adjusting the per pulse energy, and keeping the laser beam cross section on target constant. While the per pulse laser fluences were 8, 13, 19 and 22  $\text{J}/\text{cm}^2$ , the ablation time was fixed at 10 min in each experiment. Figure 1(b) shows 3 vials with,  $\text{H}_2\text{O}_2$  solution (left vial),  $\text{ZnO}_2$  based colloidal peroxide solution obtained at a per pulse laser fluence of 22  $\text{J}/\text{cm}^2$  by laser ablation (center vial) and the sediment formed at the bottom in the  $\text{ZnO}_2$  based colloidal peroxide solution (above mentioned), when it was left to rest for one hour (right vial). Figure 2(b) shows a milky solution very similar to that obtained and described by Gondal *et al.* [11-12]. Figure 2(c) shows that  $\text{ZnO}_2$  NPs are not stable, a sediment at the bottom of the vial was formed.

### 2.2. Sample characterization

The samples were characterized by Raman microspectroscopy, Calorimetry and TEM. To study the thermal stability of the as-obtained samples a calorimetry equipment (TA Instruments, SDT Q600) was used. Measurements within the range of RT to 550 °C, at a heating rate of 20°C/min under nitrogen atmosphere were performed. Raman spectra were collected by using a microRaman system (Jobin Yvon Horiba, LABRAM HR-800). A 5 mW CW Nd:YAG laser emitting at 532 nm was used to excite the samples. The objective lens of 50 X was used to focus down the laser beam on the sample and at the same time to collect the scattered light. The Raman spectra were the result over 100 acquisitions of 5 s each one. All the samples were prepared in the same manner by drying some drops of the colloidal solution on a glass slide at room temperature. TEM micrographs were obtained with a Transmission Electron Microscope (JEOL-2100). The samples were prepared by putting some drops of colloidal solution on a carbon coated copper grid.

## 3. Results and discussion

Figure 2(a-d) shows Raman spectra corresponding to the samples prepared at a per pulse laser fluences of 8, 13, 19 and 22  $\text{J}/\text{cm}^2$ . Spectra for the four samples are similar and present peaks at 410, 473 and 842  $\text{cm}^{-1}$ . These Raman peaks have been reported by some research groups like Haixin Bai *et al.* [23] and Guipeng Feng *et al.* [10] for  $\text{ZnO}_2$  powder.

**Table 1.** Raman frequencies for ZnO<sub>2</sub> NPs obtained in our work and some taken from the literature.

Escobedo-Morales et al. [17]	Feng et al. [10]	Yang et al. [13]	Our work
410	411	414	410
475	472	477	478
			555
840	838	844	842
937	936		960


Laser fluence might be expected to have an effect on ablation products, as it has been shown by Devaux et al. [24] to be related to the plasma pressure via an experimentally proven analytical model. This relationship is given, assuming constant laser energy  $I(t)=I_0$  throughout the pulse duration, by the following equation:

$$P = \sqrt{\frac{\alpha Z I_0}{2\alpha + 3}}$$


where  $P$  is the plasma pressure (constant) in GPa,  $I_0$  is the laser intensity in GWcm<sup>-2</sup>,  $\alpha$  is a correction factor of  $P$ , and  $Z$  is related to the shock impedance of each material in gcm<sup>-2</sup>s<sup>-1</sup>. Hence laser fluence is related to the square of the pressure, which may have an effect on ablation products via the conditions present during formation. The plasma energy could be further increased because of laser-supported absorption by the plasma plume. The initial experimental trial was conducted by varying laser fluence with fixed short ablation time (10 min) and 30% H<sub>2</sub>O<sub>2</sub> solution. The Raman spectra of ZnO<sub>2</sub> nanostructures outlined in figure 2 indicate that laser fluence, indeed, has not some effect on the ablated product. For both, low and high per pulse laser fluences (8 and 22 J/cm<sup>2</sup>) no particular differences in the Raman spectra can be observed, probably due to an insufficient difference in laser fluence. In the present case, it should be expected that at high reaction rates (i.e., for longer ablation times and/or higher laser fluence) well-controlled ZnO<sub>2</sub> NPs could be more readily produced because of a rapid increase in supersaturation and continuous supply of reaction groups over a long period of time.

The TGA-DSC profile of a sample obtained at a per pulse laser fluence of 22 J/cm<sup>2</sup> is showed in figure 3. In the range of RT to 500 °C, we have considered three regions for the TG curve as shown in figure 3. In the first region, one can observe a weight decrease of 3.4% from RT to 100 °C, that is due to desorption of physisorbed water in the ZnO<sub>2</sub> sample. From 100 to 200 °C a weight loss of 5 % is present. This is related with the elimination of functional groups like OH and CO<sub>3</sub>. In the third region (200 to 550 °C), it can observe a final weight loss of 18 % corresponding to the release of oxygen in the decomposition process of ZnO<sub>2</sub>

according with the reaction:  $2ZnO_2 \xrightarrow{\Delta} 2ZnO + 2O$ . In the DSC profile (figure 3), we observe that in the 200 - 550 °C range, an exothermic peak (with the maximum at 256 °C) is



**Figure 3.** (a) TGA-DSC profiles of ZnO<sub>2</sub> obtained by LALS at a per pulse laser fluence of 22 J/cm<sup>2</sup>. (b) Raman spectrum of the powder thermally treated in the calorimeter.



**Figure 4.** TEM image of ZnO<sub>2</sub> NPs synthesized by LALS at a per pulse laser fluence of 22 J/cm<sup>2</sup>. (a) TEM, Inset: sizes distribution (b) HR-TEM. Inset: the interplanar distance measured from the filtered image.

present. This exothermic peak indicates that in this temperature range, the two following phenomena give rise: 1) liberation of oxygen and 2) a transformation from c-ZnO<sub>2</sub> to w-ZnO crystals. This result is in good agreement with those reported by other authors [1, 7]. We have done the Raman analysis to the sample thermally treated in the calorimeter. The presence of a peak at 438 and a band at 582 cm<sup>-1</sup> in the Raman spectrum (Fig. 3b) are assigned to the ZnO [25], confirming the transformation of ZnO<sub>2</sub> to ZnO.

Fig. 4(a) shows TEM micrographs as well as a histogram of the size distribution of ZnO<sub>2</sub> NPs (inset) obtained at a per pulse laser fluence of 22 J/cm<sup>2</sup>. In figure 4(b) a HRTEM micrograph of the ZnO<sub>2</sub> NPs and the insets were obtained by using the filtered image. This allows us to determine the interplanar distances of 0.24 nm y 0.28 nm corresponding to the planes (200) and (111) for the cubic structure of ZnO<sub>2</sub>, respectively.

#### 4. Conclusions

In this work we have characterized ZnO<sub>2</sub> NPs obtained by Laser Ablation of Solids in Liquids. We have showed that by using the fundamental wavelength (1064 nm) of a Nd:YAG laser, a Zn disk as target and H<sub>2</sub>O<sub>2</sub> (30 %) as liquid media, it is possible to obtain ZnO<sub>2</sub> NPs. Raman results agree well with that reported in the literature. We have obtained NPs 11-14 nm in size. These ZnO<sub>2</sub> NPs suffered thermal decomposition in the range of 200-500 °C giving ZnO as resultant material. The work presented and discussed here confirms LASL as an easy, “green”, fast and efficient technique for the synthesis of ZnO<sub>2</sub> NPs, being (besides chemical methods), another route of synthesis to produce zinc-based nanomaterials.

#### Acknowledgements

E. Palma-Palma thanks to CONACyT for financing the Master Studies. We thank to Dr. E. Camps-Carvajal and Dr. S. Hernández-López for Raman and calorimetry measurements, respectively.

#### References

- [1] Y. Wolanov, P. V. Prikhodchenko, A. G. Medvedev, R. Pedahzur, O. Lev, Environ. Sci. Technol., **47**, 8769 (2013).
- [2] R. Colonia, J. L. Solís and M. Gómez, Adv. Nat. Sci.: Nanosci. Nanotechnol., **5**, 015008 (2014).
- [3] S. Verma, S. L. Jain, Inorg. Chem. Front., **1**, 534 (2014).
- [4] M. Sun, W. Hao, C. Wang, T. Wang, Chem. Phys. Lett., **443**, 342 (2007).
- [5] R. Colonia S., M. M. Gómez L., K. León, J. L. Solís, V., Rev. Per. Quím. Ing. Quím. **13**, 52 (2010).
- [6] W. Chen, Y. H. Lu, M. Wang, L. Kroner, H. Paul, H.-J. Fecht, J. Bednarcik, K. Stahl, Z. L. Zhang, U. Wiedwald, U. Kaiser, P. Ziemann, T. Kikegawa, C. D. Wu, J. Z. Jiang, J. Phys. Chem. C, **113**, 1320 (2009).
- [7] K. Kyung-A, C. Jae-Ryung, G. Myoung-Seon, and K. Jong-Gyu, Bull. Korean Chem. Soc. **35**, 431 (2014).
- [8] Escobedo-Morales, R. Esparza, A. García-Ruiz, A. Aguilar, E. Rubio-Rosas, R. Pérez, Journal of Crystal Growth, **316**, 37 (2011).
- [9] T. Hong Guo, Y. Liu, Y. Cai Zhang, M. Zhang, Mater. Lett., **65**, 639 (2011).
- [10] G. Feng, L. Yang, T. Wang, J. Zhang, T. Lou, Particuology, **10**, 388 (2012).
- [11] M. A. Gondal, Q.A. Drmosh, Z.H. Yamani, T.A. Saleh, Appl. Surf. Sci. **256**, 298 (2009).
- [12] Q. A. Drmosh, M.A. Gondal, Z.H. Yamani, T.A. Saleh, Appl. Surf. Sci. **256**, 4661 (2010).
- [13] L. Y. Yang, G. Feng, T. X. Wang, Mater. Lett., **64**, 1647 (2010).
- [14] T. Xi Wang, T. Jun Lou, Mater. Lett., **62**, 2329 (2008).
- [15] S. Cheng, D. Yan, J.T. Chen, R.F. Zhuo, J. Feng, H. J. Li, H. T. Feng, P. X. Yan, J. Phys. Chem., C **113**, 13630 (2009).
- [16] E. Redel, C. Huai, O. Dag, S. Petrov, P. G. O'Brien, M. G. Helander, J. Mlynarski, G. A. Ozin, Small, **8**, 3806 (2012).
- [17] A. Escobedo-Morales, D. Téllez-Flores, Ma. De Lourdes Ruiz Peralta, J. García-Serrano, Ana M. Herrera-González, E. Rubio-Rosas, E. Sánchez-Mora, O. Olivares Xometl, Mat. Chem. and Phy., **151**, 282 (2015).
- [18] Haibo Zeng , Xi-Wen Du , Subhash C. Singh , Sergei A. Kulich , Shikuan Yang , Jianping He , and Weiping Cai, Adv. Funct. Mater., **22**, 1333 (2012).
- [19] Adel K. Mahmoud, Zainab Fadhill, Suha Ibrahim Al-nassar, Furat Ibrahim Husein, Erhan Akman and Arif Demir, Journal of Materials Science and Engineering, **B 3 (6)**, 36, (2013).
- [20] M. Maaza B. D. Ngom S. Khamlich, J. B. Kana Kana P. Sibuyi D. Hamidi, S. Ekambararam, J Nanopart Res **14**, 1 (2012).
- [21] Gondal, M. A.; Saleh, Tawfik A.; Drmosh, Q., Science of Advanced Materials, **4**, 507 (2012).
- [22] Manish Kumar Singh , Mohan Chandra Mathpal, Arvind Agarwal, Chemical Physics Letters, **536**, 87 (2012).
- [23] Haixin Bai, Xiaohua Liu, Materials Letters, **64**, 341 (2010).
- [24] R. Fabbro, J. Fournier, P. Ballard, D. Devaux, and J. Virmont, J. Appl. Phys., **68**, 2 (1990).
- [25] P. E Acuña-Avila, R. López, E. Vigueras-Santiago, S. Hernández-López, M. Camacho-López, C. Ornelas-Gutierrez, W. Antunez, AIP Advances, **5**, 0671091 (2015).